

MINT

SANDSTONE



DESCRIPTION: Quarried in Madhya Pradesh, India, Mint sandstone comes with bright colour and a very soothing variation range that enhances the beauty of the place. It combines natural high slip resistance with strength, making it suitable for both pedestrian and trafficked areas. Both quarry and the manufacturing works are accredited with ISO 9001:2015 and SA 8000:2014 certification by TUV Rheinland, Germany.

APPLICATIONS


INTERIOR FLOOR	INTERIOR WALL	SHOWER WALL	SHOWER FLOOR	EXTERIOS FLOOR	EXTERIOR WALL	POOL/ FOUNTAIN	COUNTERTOP
√	√			√	√	√	



SUMMARY OF KEY TECHNICAL DATA

STANDARD	TEST	RESULT
EN 12440 : 2001	Place of origin	Madhya Pradesh, India
EN 12440 : 2001	Petrographic examination	Sandstone
EN 13755 : 2008	Determination of water absorption at atmospheric pressure %	2.7 +/- 1.0
EN 1926	Determination of compressive strength	71 +/- 14.0 mpa
EN 12371	Determination of frost resistance	59.0 +/- 13.0 mpa
EN 14157	Determination of abrasion resistance	22.3 +/- 1.4 Groove length
EN 14231	Determination of slip resistance; Dry	73 +/- 2.4
EN 14231	Determination of slip resistance; Wet	50 +/- 3.0

VARIATIONS



INSTALLATION & MAINTENANCE

GROUTING	SEALER	LAYOUT	DRY LAYOUT	BASE
5-10 mm	RECOMMENDED			FULL MORTAR BED 4 TO 1 MIX

PROJECT IMAGE

